FILM DATA SHEET



1435 S GROVE AVE #1 ONTARIO, CA 91761-4590 (844) 857-8277 PackFreshUSA.com

Exterior

48 Gauge Metalized PET

2.5 mil LLDPE
Interior

Physical Description:

Silver 3 mil metalized PET/poly laminated barrier film

Application:

PF300MET is an FDA approved film typically used in food, medical, and general industrial applications. The metalization of the PET reduces OTR and MVTR to extend shelf-life and protect the product from environmental factors. The LDPE sealant layer enables this laminated structure to be heat-sealed for granola, candy, chips,... etc that need longer shelf-life than is typically provided by clear barrier structures.

Converting:

It can be converted in many ways: 2-seal pouch, 3-seal pouch, stand-up pouch, tubing, or a recloseable zippered pouch (tamper-evident or open top). It can also be surface printed or reverse trapped, and is available in web widths up to 60 inches.

Physical Properties:

PROPERTIES	TEST METHOD	UNIT OF MEASURE	TYPICAL VALUE
CALIPER		mils	3.0
MVTR	MOCON	g/100in ² 24 hrs.	0.032
OTR	ASTM-1434-66	cc/100in ² /24 hrs.	0.04

The values indicated in this document are the results of tests made in compliance with normal standards. They are given as an indication and should be considered as average values. Safeguard Brands, Inc. and PackFreshUSA make no warranty, expressed or implied, as to the suitability of these materials for any specific use. The values shown above were developed from random samples taken from production material. Actual values may vary somewhat from those depicted here. Customers should determine product suitability for their applications based upon their own testing and internal criteria.